

PRECAUTIONS:

Combustible Liquid (Flash point 108° F). Keep away from open flame and heat. Do not smoke. Avoid direct contact. Skin and eye irritation may occur. Use in well-ventilated area. Inhalation of vapors may cause breathing difficulties.

KEEP OUT OF REACH OF CHILDREN.

Recommended for exterior use only.

FIRST AID:

Eye contact: Move victim from exposure source. Flush eyes with water for 10-15 minutes. Skin: Remove contaminated clothing. Wash with soap and water. If irritation persists seek medical attention. Inhalation: Move victim to fresh air immediately. Contact physician if breathing is difficult.

FOR CHEMICAL EMERGENCY

Spill, Leak, Fire, Exposure or Accident

CALL INFOTRAC: Day or Night

800-535-5053

OUTSIDE THE UNITED STATES CALL COLLECT 1-352-323-3500

HMS: Health - 1 Flammability - 2 Reactivity - 0

FOR PROFESSIONAL USE ONLY!

DO NOT THIN!

VOC CONTENT: Less than 700 g/L, unless stated

DOT: Not Regulated (Unless 350 VOC Formula)

Coating may darken surface.

Coating may cause surface to be a slip hazard or slippery when wet. A slip resistant additive such as Surf-Grip may be added to help prevent slip hazards.

Please refer to msds & technical data sheet prior to use of this product.

ATTENTION:

This container is hazardous when empty. Empty containers retain product residues (vapor and liquid). All labeled precautions must be observed. Do not re-use empty container for any purpose until commercially cleaned or reconditioned. Store empty container away from heat, sparks, and flame. Dispose of empty container according to state and federal laws. Clean up with Xylene.

WARRANTY:

Surface Koatings, Inc. warrants our products to be of good quality, free of defects and will conform with our published specifications in force on the date of acceptance of the order. As the exclusive remedy for breach of this warranty, we will replace defective materials. Ninety days after Surface Koatings, Inc. has shipped the products, all our warranty and other duties with respect to the quality of the materials delivered shall conclusively be presumed to have been satisfied, all liability therefore terminates, and no action for breach of any said duties may thereafter be commenced. No warranty is expressed or implied as to the length of life of this product, or merchantability or fitness. Liability, if any, is limited to the purchase price of the material. Under no circumstances will Surface Koatings, Inc. be liable for a consequential damage to anyone in excess of the purchase price of the products.

SHELF LIFE:

Up to two years in unopened container stored at room temperature.

STAMP SEAL 30



High Performance Decorative Concrete Sealer Meets Cure & Seal Specifications



SURFACE PREPARATION:

Concrete surface must be clean and free of all contaminants and water. Do not apply if rain is forecast within 24 hours. If moisture is present or if the surface is not clean and free of all contaminants, the sealer may have white spots and have premature delamination and failure.

Substrate temperature must be no less than 50 degrees F and not exceed 80 degrees F. If applied outside these limits the sealer may not achieve adequate film formation and may have excessive air entrapment, bubbles, blushing or hazing. Note that in direct sunlight, substrate temperature can exceed 150 degrees F which can cause extreme bubbling issues.

MIXING:

Stir well before using. Material may separate during long term storage.

APPLICATION:

Apply using a 3/8" - 1/2" nap roller cover using long even uniform strokes at approximately 200-350 square feet per gallon depending on porosity and texture of substrate. A Chapin style solvent resistant sprayer is not recommended for this sealer due to high content of solids. Thick or puddle areas may prevent the solvent from evaporating and may be susceptible to moisture intrusion which may cause milky white spots. Applying too thin may cause sealer to prematurely delaminate, flake or wear away. Allow sealer to dry for 24 hours for light traffic and at least 48 hours for heavy traffic. If applying two coats, wait approximately 4 - 6 hours between coats.

PLEASE NOTE:

It is always recommended to test the product in a small, inconspicuous area (on the same concrete sub-strate) for desired results prior to application. Coverage rates may vary for all coatings and substrates depending on porosity, density, texture etc. If applying by spray method, extended coverage rates may be achieved, but be aware that less material will be applied and inadequate film formation or performance expectations may be limited. DO NOT USE ON BRICK.

Solids	30%
Drying Time	1 - 2 hours
Re-Coat Time	4 - 24 hours
Foot Traffic	4 - 6 hours
Wheel Traffic	24 - 48 hours
Application Temp	50° F - 80° F
Wet Appearance	Clear
Dry Appearance	Clear & Super High Gloss
VOC Content	<700 g/l or <350 g/l if stated
Blush Resistance	Good
Solvent Resistance	Minimal
Concrete Adhesion	Excellent

*Please note that low air and/or concrete temperatures and/or relative humidity may extend drying times. Follow recommended coverage rates for best results.

www.con-cretewerks.com

Made in the USA